



**GEOTEX**<sup>®</sup> 1201 is a polypropylene, staple fiber, needlepunched nonwoven geotextile produced by Propex, and will meet the following Minimum Average Roll Values (MARV) when tested in accordance with the methods listed below. The fibers are needed to form a stable network that retains dimensional stability relative to each other. The geotextile is resistant to ultraviolet degradation and to biological and chemical environments normally found in soils.

**GEOTEX 1201** conforms to the property values listed below<sup>1</sup>. Propex performs internal Manufacturing Quality Control (MQC) tests that have been accredited by the Geosynthetic Accreditation Institute – Laboratory Accreditation Program (GAI-LAP).

			MARV <sup>2</sup>
PROPERTY	TEST METHOD	ENGLISH	METRIC
<b>ORIGIN OF MATERIALS</b>			
% U.S. Manufactured Inputs		100%	100%
% U.S. Manufactured		100%	100%
<b>PHYSICAL</b>			
Mass Per Unit Area (Typical)	ASTM D-4632	12.0 oz/yd <sup>2</sup>	407 g/m <sup>2</sup>
<b>MECHANICAL</b>			
Tensile Strength (Grab)	ASTM D-4632	305 lbs	1357 N
Elongation	ASTM D-4632	50%	50%
CBR Puncture	ASTM D-6241	825 lbs	3671 N
Mullen Burst	ASTM D-3786	580 psi	3998 kPa
Trapezoidal Tear	ASTM D-4533	115 lbs	512 N
<b>ENDURANCE</b>			
UV Resistance % Retained at 500 hrs	ASTM D-4355	70%	70%
<b>HYDRAULIC</b>			
Apparent Opening Size (AOS) <sup>3</sup>	ASTM D-4751	100 US Std. Sieve	0.150 mm
Permittivity	ASTM D-4491	1.0 sec <sup>-1</sup>	1.0 sec <sup>-1</sup>
Water Flow Rate	ASTM D-4491	75 gpm/ft <sup>2</sup>	3056 l/min/m <sup>2</sup>
<b>ROLL SIZES</b>		15 ft x 300 ft	4.57 m x 91.5 m

**NOTES:**

1. The property values listed above are effective 04/2011 and are subject to change without notice.
2. Values shown are in weaker principal direction. Minimum average roll values (MARV) are calculated as the typical minus two standard deviations. Statistically, it yields a 97.7% degree of confidence that any samples taken from quality assurance testing will exceed the value reported.
3. Maximum average roll value.



TESTED. PROVEN. TRUSTED.  
[www.geotextile.com](http://www.geotextile.com)

**Propex Operating Company, LLC** · 6025 Lee Highway, Suite 425 · PO Box 22788 · Chattanooga, TN 37422

ph 423 899 0444 · ph 800 621 1273 · fax 423 899 7619

Geotex<sup>®</sup>, Landlok<sup>®</sup>, Pyramat<sup>®</sup>, X3<sup>®</sup>, SuperGro<sup>®</sup>, Petromat<sup>®</sup> and Petrotac<sup>®</sup> are registered trademarks of Propex Operating Company, LLC.

This publication should not be construed as engineering advice. While information contained in this publication is accurate to the best of our knowledge, Propex does not warrant its accuracy or completeness. The ultimate customer and user of the products should assume sole responsibility for the final determination of the suitability of the information and the products for the contemplated and actual use. The only warranty made by Propex for its products is set forth in our product data sheets for the product, or such other written warranty as may be agreed by Propex and individual customers. Propex specifically disclaims all other warranties, express or implied, including without limitation, warranties of merchantability or fitness for a particular purpose, or arising from provision of samples, a course of dealing or usage of trade.