

## PRODUCT DATA • GEOTEX 350ST

**GEOTEX 350ST** is a woven polypropylene geotextile containing heavy woven tape/fibrillated yarns produced by Propex, and will meet the following Minimum Average Roll Values (MARV) when tested in accordance with the methods listed below. These characteristics make **GEOTEX 350ST** ideal for the construction of embankments over soft soils, steepened slopes, and modular block and/ or wrapped-face retaining walls. The geotextile is resistant to ultraviolet degradation and to biological and chemical environments normally found in soils.

**GEOTEX 350ST** conforms to the property values listed below<sup>1</sup>, as well as meets the requirements set forth by AASHTO M-288/NTPEP (Geotextile Specification for Highway Application). Propex performs internal Manufacturing Quality Control (MQC) tests that have been accredited by the Geosynthetic Accreditation Institute – Laboratory Accreditation Program (GAI-LAP).

## MARV<sup>2</sup>

	1417 (1.4.4		
PROPERTY	TEST METHOD	ENGLISH	METRIC
ORIGIN OF MATERIALS			
% U.S. Manufactured Inputs		100%	100%
% U.S. Manufactured		100%	100%
MECHANICAL			
Tensile Strength (Grab)	ASTM D-4632	450 x 350 lbs	2002 x 1557 N
Elongation	ASTM D-4632	15%	15 %
Wide Width Tensile	ASTM D-4595	3600 x 3240 lbs/ft	52.6 x 47.3 kN/m
Wide Width Elongation	ASTM D-4595	8%	8%
Wide Width Tensile at 5% Strain	ASTM D-4595	1356 lbs/ft	19.8 kN/m
CBR Puncture	ASTM D-6241	1200 lbs	5337.9 N
Trapezoidal Tear	ASTM D-4533	130 lbs	578.3 N
ENDURANCE			
UV Resistance % Retained at 500 hrs	ASTM D-4355	70%	70%
HYDRAULIC			
Apparent Opening Size (AOS) <sup>3</sup>	ASTM D-4751	30 US Std. Sieve	0.600 mm
Permittivity	ASTM D-4491	0.35 sec <sup>-1</sup>	0.35 sec <sup>-1</sup>
Water Flow Rate	ASTM D-4491	30 gpm/ft <sup>2</sup>	1224 lpm/m <sup>2</sup>
ROLL SIZES		15.0 ft x 300 ft 12.5 ft x 300 ft	4.6 m x 91.5 m 3.8 m x 91.5m

## NOTES:

- 1. The property values listed above are effective 04/2011 and are subject to change without notice.
- 2. Values shown are in weaker principal direction. Minimum average roll values (MARV) are calculated as the typical minus two standard deviations. Statistically, it yields a 97.7% degree of confidence that any samples taken from quality assurance testing will exceed the value reported.
- 3. Maximum average roll value.



Propex Operating Company, LLC · 1110 Market Street, Suite 300 · Chattanooga, TN 37402 USA

PH: 800-621-1273 · F: 423-899-5005 · PropexGlobal.com

Fibermesh®, Fibercast®, Enduro®, Novomesh®, Novomesh®, Novomesh®, Novomesh®, Novomesh®, Novomesh®, Novomesh®, Petrotac®, And Reflectex™ are registered trademarks of Propex Operating Company, LLC.

This publication should not be construed as engineering advice. While information contained in this publication is accurate to the best of our knowledge, Propex does not warrant its accuracy or completeness. The ultimate customer and user of the products should assume sole responsibility for the final determination of the suitability of the information and the products for the contemplated and actual use. The only warranty made by Propex for its products is set forth in our product data sheets for the product, or such other written warranty as may be agreed by Propex and individual customers. Propex specifically disclaims all other warranties, express or implied, including without limitation, warranties of merchantability or fitness for a particular purpose, or arising from provision of samples, a course of dealing or usage of trade.